

H·FLOR

PRESTG XL

LX Hausys America, Inc.

900 Circle 75 Parkway, Suite 1500 Atlanta, GA 30339 866-544-4622

www.lxhausys.com

COLLECTION NAME PRESTG XL
SELLING STYLE #(s) PRESTG XL
TOTAL # SKU'S(COLORS) 12

PRODUCT SPECIFICATIONS / CONTENT / CERTIFICATIONS

Thickness	6.0mm (0.236 in)	with 1.5mm IXPE Foam
Wear Layer	20mil (0.5mm)	
Glass Fiber	None	
Finishing / Coating	Stoneshield	
Nominal Dimensions (inches & mm)	9" x 60" (228.6 x 1523 mm)	
Actual Dimensions (inches & mm)	9" x 60" (228.6 x 1523 mm)	
Bevel	Micro-Beveled	
Class / ASTM F3261	Class I - Type B(embossed), Grade 1, Backing Class B	
Backing	IXPE Foam	
Gloss Level	5~12	
Classification	Residential / Commercial	
Added Antimicrobial	No	
Backstamp info	None	
CE Certification	Yes	

PACKING SPEC'S

PACKING SPEC S			
Product dimension (Width, inch & mm)	9" (228.6 mm)		
Product dimension (Length, inch & mm)	60" (1523 mm)		
Pallet Dimensions (L x W x H)	1,600 X 1,000 x 148 mm		
Square feet per plank/tile	3.748		
Square feet per carton	29.981		
Square feet per pallet	1,678.91		
Square feet per container	23,504.76	20 foot container	
Weight per sq ft(lbs)	1.745		
Weight per plank/tile (lbs)	6.54		
Weight per carton (lbs)	52.324		
Weight per pallet (lbs)	2,930.12		
Weight per container (lbs)	41,021.69		
Pieces per box	8		
Boxes per pallet	56		
Box Type	Corrugated		
Pallet per container	14		
Boxes per container	784		

PRODUCT PERFORMANCE / TESTING

ASTM F2055 Size	Passes	As specified ± 0.016 in
ASTM F387 Thickness	Passes	As specified ± 0.008 in (wigh foam
ASTM F2055 Squareness	Passes	Max. 0.010 in.
ASTM F1914 Residual Indentation	Passes	Avg.≤0.007 in. (0.18mm)
ASTM F2199 Dimension Stability	Passes	< 0.2%/ lineal ft(305mm)
ASTM F2199 Dimension Stability	Passes	Max. 0.080 in. (2mm)
ASTM F1914 Surface integrity	Passes	No puncture through wear layer /deco into rigid core
ASTM F925 Chemical Resistance	Passes	No change
ASTM F1514 Resistance to Heat	Passes	< 8 (delta E) avg.
ASTM F1515 Resistance to Light	Passes	< 8 (delta E) avg.
ASTM E648 Critical Radiant Flux	Class 1	Class 1 (>0.45 W/c m²)
ASTM E662 Optical Smoke Density	Passes	< 450
ASTM C1028 Slip Resistance	Passes	ADA Compliant(> 0.50)
ASTM F970 Static Load	Passes (500 psi with Foam)	250 psi(<0.005")

TECHNICAL INFORMATION / DOCUMENTS

Installation Method	Click
Recommended Adhesive(s)	No Adhesives
Polished Required (Y/N)	None
Product Warranty	Lifetime for Residential, 10 Years for Commercial

 $[\]mbox{\ensuremath{^{\star}}}$ The warranty covers manufacturing defects and wear-out in the ordinary exercise of due care.









